

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 July 2003 (10.07.2003)

PCT

(10) International Publication Number
WO 03/056099 A1

- (51) International Patent Classification⁷: **D21H 17/68**, 21/10 (74) Agent: **RIGLER, Johann**; Eka Chemicals AB, Patent Department, P.O. Box 11556, S-100 61 Stockholm (SE).
- (21) International Application Number: **PCT/SE02/02444** (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date:
20 December 2002 (20.12.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
01850224.5 21 December 2001 (21.12.2001) EP
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): **AKZO NOBEL N.V.** [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL).
- (71) Applicant (*for SE only*): **EKA CHEMICALS AB** [SE/SE]; S-445 80 Bohus (SE).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **JOHANSSON-VESTIN, Hans** [SE/SE]; Madängsgatan 5, S-442 33 Kungälv (SE). **NYANDER, Johan** [SE/SE]; Jordgränd 29, S-192 74 Sollentuna (SE). **NORDIN, Jan** [SE/SE]; Gamlavägen 94, S-862 32 Kvissleby (SE).
- Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **AQUEOUS SILICA-CONTAINING COMPOSITION AND PROCESS FOR PRODUCTION OF PAPER**

(57) Abstract: The present invention relates to an aqueous silica-containing composition comprising an anionic organic polymer having at least one aromatic group and anionic aggregated or microgel formed silica-based particles. The aqueous silica-containing composition contains the anionic organic polymer having at least one aromatic group and the anionic silica-based particles in an amount of at least 0.01 % by weight of the total weight of the aqueous silica-containing composition. The aqueous silica-containing composition contains substantially no cellulose-reactive sizing agent and the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate. The invention further relates to methods for the preparation of the aqueous silica-containing composition and the use of the aqueous silica-composition as a drainage and retention aid in a process for the production of paper. The invention also relates to a process for the production of paper from an aqueous suspension containing cellulosic fibres, and optionally filler, in which the aqueous silica-containing composition and at least one charged organic polymer are added to the cellulosic suspension.

WO 03/056099 A1

Aqueous silica-containing composition and process for production of paper

The present invention relates to an aqueous silica-containing composition comprising an anionic organic polymer having at least one aromatic group and anionic silica-based particles. The invention further relates to a method for the preparation of the aqueous silica-containing composition, uses of the aqueous silica-containing composition and a papermaking process.

Background of the Invention

In the papermaking art, an aqueous suspension containing cellulosic fibres, and optionally fillers and additives, referred to as stock, is fed into a headbox which ejects the stock onto a forming wire. Water is drained from the stock through the forming wire so that a wet web of paper is formed on the wire. The formed paper web is dewatered and dried in the drying section of the paper machine. Drainage and retention aids are conventionally introduced into the stock in order to facilitate drainage and to increase adsorption of fine particles onto the cellulosic fibres in such a way that the fine particles are retained with the fibres on the wire.

US 4,388,150 discloses a binder in papermaking comprising a complex of cationic starch and colloidal silicic acid to produce a paper having increased strength and improved levels of retention of added minerals and papermaking fines.

US 4,750,974 discloses a coarccervate binder for use in papermaking comprising a tertiary combination of a cationic starch, an anionic high molecular weight polymer and a dispersed silica.

US 5,368,833 discloses silica sols containing aluminium modified silica particles with high specific surface area and a high content of microgel.

US 5,567,277 discloses a composition comprising an aqueous cellulosic furnish, a high molecular weight cationic polymer and an anionic polymer comprising modified lignin.

US 6,022,449 discloses the use of water-dispersible polyisocyanates with anionic and/or potentially anionic groups and cationic and/or potentially cationic compounds in paper finishing.

EP 0 418 015 A1 discloses an active sizing composition containing an aqueous emulsion in combination with an anionic dispersant or emulsifier. By using anionic polyacrylamide, anionic starch or colloidal silica the anionic charge density in the sizing composition can be extended.

US 5,670,021 refers to a process for the production of paper by forming and dewatering a suspension of cellulose, wherein the dewatering takes place in the

presence of an alkali metal silicate and a phenolic resin added at the same point into the suspension.

US 6,033,524 discloses a method for increasing retention and drainage of filling components in a paper making furnish in a paper making process comprising adding to the furnish a slurry of filling components, also containing a phenolic enhancer.

US 6,315,824 pertains to a dispersed composition comprising a hydrophobic phase and an aqueous phase, the composition being stabilised by a cationic colloidal coacervate stabilising agent, the coacervate stabilising agent comprising an anionic component and a cationic component.

EP 0,953,680 A1 refers to a process for the production of paper from a suspension comprising adding to the suspension a cationic organic polymer.

US 5,185,062 discloses a papermaking process including the steps of adding to the papermaking slurry a high molecular weight cationic polymer and then a medium molecular weight anionic polymer.

US 4,313,790 refers to a process for the production of paper which consists of the addition to the papermaking furnish of kraft lignin or modified kraft lignin and poly(oxyethylene).

US 6,165,259 relates to an aqueous dispersion containing a dispersant and a disperse phase containing a hydrophobic material, the dispersant comprising an anionic compound and a cationic compound.

It would be advantageous to be able to provide drainage and retention aids with improved performance. It would also be advantageous to be able to provide retention and drainage aids with good storage stability. It would further be advantageous to be able to provide a papermaking process with improved drainage and/or retention performance.

The Invention

According to the present invention it has unexpectedly been found that an improved drainage and/or retention effect of a cellulosic suspension on a wire can be obtained by using an aqueous silica-containing composition comprising at least one anionic organic polymer with at least one aromatic group and anionic aggregated or microgel formed silica-based particles. The aqueous silica-containing composition is useful in processes for production of paper from all types of stocks, in particular stocks having high contents of salts (high conductivity) and colloidal substances. The aqueous silica-containing composition is also useful in papermaking processes with a high degree of white water closure, i.e. extensive white water recycling and limited fresh water supply. Hereby the present invention makes it possible to increase the speed of the paper machine

and to use a lower dosage of additives to give a corresponding drainage and/or retention effect, thereby leading to an improved papermaking process and economic benefits.

The terms "drainage and retention aid", as used herein, refer to one or more components, which when added to an aqueous cellulosic suspension, give better drainage and/or retention than is obtained when not adding the said one or more components. All types of stocks, in particular stocks having high contents of salts (high conductivity) and colloidal substances will obtain better drainage and retention performances by the addition of the composition according to the present invention. This is important in papermaking processes with a high degree of white water closure, i.e. extensive white water recycling and limited fresh water supply.

In accordance with the present invention there is provided an aqueous silica-containing composition comprising an anionic organic polymer having at least one aromatic group and anionic silica-based particles comprising aggregated or microgel formed silica-based particles. The aqueous silica-containing composition contains the anionic organic polymer having at least one aromatic group and the anionic silica-based particles, calculated as SiO_2 in an amount of at least 0.01 % by weight based on the total weight of the aqueous silica-containing composition. The composition contains substantially no cellulose-reactive sizing agent and the said anionic organic polymer is not an anionic naphthalene sulphonate formaldehyde condensate.

There is further provided an aqueous silica-containing composition obtainable by mixing an anionic organic polymer having at least one aromatic group with an aqueous alkali stabilised silica-based sol having an S-value in the range of from about 5 up to about 50% containing anionic aggregated or microgel formed silica-based particles. The obtained aqueous silica-containing composition contains the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 in an amount of at least 0.01 % by weight based on the total weight of the aqueous silica-containing composition. The composition contains substantially no cellulose-reactive sizing agent and that said anionic organic polymer is not anionic naphthalene sulphonate formaldehyde condensate.

There is further provided a method for preparation of an aqueous silica-containing composition which comprises mixing in the presence of substantially no cellulose-reactive sizing agent an anionic organic polymer having at least one aromatic group with silica-based particles comprising anionic aggregated or microgel formed silica-based particles to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition with the proviso that the anionic organic

polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

There is further provided a method for preparation of an aqueous silica-containing composition which comprises mixing an anionic organic polymer having at least one aromatic group and a charge density of at least 0.1 meq/g of dry polymer, with silica-based particles comprising anionic aggregated or microgel formed to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition, with the proviso that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

There is further provided a method for preparation of an aqueous silica-containing composition which comprises desalinating an aqueous solution of an anionic organic polymer having at least one aromatic group, mixing in the desalinated anionic organic polymer having at least one aromatic group with silica-based particles comprising anionic aggregated or microgel formed silica-based particles to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the aggregated or microgel formed silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition with the proviso that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

There is further provided an aqueous silica-containing composition obtainable by the methods according to the invention.

The invention further relates to the use of the aqueous silica-containing composition of the invention, as flocculating agent in combination with at least one cationic organic polymer in the production of pulp and paper and for water purification.

According to the invention there is further provided a process for the production of paper from a suspension containing cellulosic fibres, and optionally fillers, comprising adding to the suspension at least one cationic organic polymer and an aqueous silica-containing composition according to the invention.

The aqueous silica-containing composition comprises at least one anionic organic polymer with at least one aromatic group, which is not an anionic naphthalene sulfonate formaldehyde condensate. The aromatic group of the anionic polymer can be present in the polymer backbone or in a substituent group that is attached to the polymer backbone (main chain). Examples of suitable aromatic groups include aryl, aralkyl and alkaryl groups and derivatives thereof, e.g. phenyl, tolyl, naphthyl, phenylene, xylylene,

benzyl, phenylethyl and derivatives of these groups. The anionically charged groups can be present either in the anionic polymer or in the monomers used for preparing the anionic polymer. The anionically charged groups can either be groups carrying an anionic charge or acid groups carrying an anionic charge when dissolved or dispersed in water.

5 These groups are herein collectively being referred to as anionic groups, such as phosphate, phosphonate, sulphate, sulphonic acid, sulphonate, carboxylic acid, carboxylate, alkoxide and phenolic groups, i.e. hydroxy-substituted phenyls and naphthyls. Groups carrying an anionic charge are usually salts of an alkali, alkaline earth metals or ammonia.

10 Anionic polymers containing one or more aromatic groups according to the invention can suitably be selected from the group consisting of step-growth polymers, chain-growth polymers, polysaccharides and naturally occurring aromatic polymers. The term "step-growth polymer", as used herein, refers to a polymer obtained by step-growth polymerisation, also being referred to as step-reaction polymer and step-reaction
15 polymerisation, respectively. Preferably the anionic polymer is a step-growth polymer. The anionic polymers according to the invention can be linear, branched or cross-linked. Preferably the anionic polymer is water-soluble or water-dispersible.

Examples of suitable anionic step-growth polymers according to the present invention include condensation polymers, i.e. polymers obtained by step-growth condensation
20 polymerisation, e.g. condensates of an aldehyde such as formaldehyde with one or more aromatic compounds containing one or more anionic groups, and optional other comonomers useful in the condensation polymerisation such as urea and melamine. Examples of suitable aromatic compounds containing anionic groups comprises compounds containing anionic groups such as phenolic compounds, e.g. phenol,
25 resorcinol and derivatives thereof, aromatic acids and salts thereof.

Examples of suitable anionic step-growth polymers according to the present invention include addition polymers, i.e. polymers obtained by step-growth addition polymerisation, e.g. anionic polyurethanes prepared from a monomer mixture comprising aromatic isocyanates and/or aromatic alcohols. Examples of suitable aromatic isocyanates
30 include diisocyanates, e.g. toluene-2,4- and 2,6-diisocyanates and diphenylmethane-4,4'-diisocyanate. Examples of suitable aromatic alcohols include dihydric alcohols, i.e. diols, e.g. bisphenol A, phenyl diethanol amine, glycerol monoterephthalate and trimethylolpropane monoterephthalate. Monohydric aromatic alcohols such as phenol and derivatives thereof may also be employed. The monomer mixture can also contain non-aromatic isocyanates
35 and/or alcohols, usually diisocyanates and diols, for example any of those known to be useful in the preparation of polyurethanes. Examples of suitable monomers containing anionic groups include the monoester reaction products of triols, e.g. trimethyloethane, tri-

methylopropane and glycerol, with dicarboxylic acids or anhydrides thereof, e.g. succinic acid and anhydride, terephthalic acid and anhydride, such as glycerol monosuccinate, glycerol monoterephthalate, trimethylolpropane monosuccinate, trimethylolpropane monoterephthalate, N,N-bis-(hydroxyethyl)-glycine, di-(hydroxymethyl)propionic acid, N,N-bis-(hydroxyethyl)-2-aminoethanesulfonic acid, and the like, optionally and usually in combination with reaction with a base, such as alkali and alkaline earth metal hydroxides, e.g. sodium hydroxide, ammonia or an amine, e.g. triethylamine, thereby forming an alkali, alkaline earth metals or ammonium counter-ion.

Examples of suitable anionic chain-growth polymers according to the invention include anionic vinyl addition polymers obtained from a mixture of vinylic or ethylenically unsaturated monomers. The mixture of vinylic or ethylenically unsaturated monomers comprises at least one monomer having an aromatic group and at least one monomer having an anionic group. Usually the monomers are co-polymerised with non-ionic monomers such as acrylate- and acrylamide-based monomers. Examples of suitable anionic monomers include (meth)acrylic acid and paravinyl phenol (hydroxy styrene).

Examples of suitable anionic polysaccharides with at least one aromatic group include starches, guar gums, cellulose derivatives, chitins, chitosans, glycans, galactans, glucans, xanthan gums, pectins, mannans, dextrans, preferably starches, and guar gums, suitable starches including potato, corn, wheat, tapioca, rice, waxy maize and barley, preferably potato. The anionic groups in the polysaccharide can be native and/or introduced by chemical treatment. The aromatic groups in the polysaccharide can be introduced by chemical methods known in the art.

Examples of suitable (modified) naturally occurring aromatic anionic polymers of this invention include lignosulphonates, Kraft lignins, oxylignins, and tannin extracts i.e. naturally occurring polyphenolic substances that are obtained from the sulphite or sulphate pulp processes or from extracts of bark.

The weight average molecular weight of the anionic polymer can vary within wide limits dependent on, inter alia, the type of polymer used, and usually it is at least about 500, suitably above about 800 and preferably above about 1,000. The upper limit is not critical; it can be about 10,000,000, usually 1,000,000, suitably 500,000, preferably 200,000 and most preferably 100,000.

The anionic polymer can have a degree of anionic substitution (DS_A) varying over a wide range dependent on, inter alia, the type of polymer used. DS_A is usually from 0.01 to 2.0, suitably from 0.02 to 1.8 and preferably from 0.025 to 1.5; and the degree of aromatic substitution (DS_Q) can be from 0.001 to 1.0, usually from 0.01 to 0.8, suitably from 0.02 to 0.7 and preferably from 0.025 to 0.5. In case the anionic polymer contains cationic groups, the degree of cationic substitution (DS_C) can be, for example, from 0 to

0.2, suitably from 0 to 0.1 and preferably from 0 to 0.05, the anionic polymer having an overall anionic charge. Usually the anionic charge of the anionic polymer is within the range of from 0.1 to 10.0 meq/g of dry polymer, suitably from 0.2 to 6.0 meq/g, and preferably from 0.5 to 4.0 meq/g.

5 The aqueous silica-containing composition according to the invention also comprises anionic aggregated or microgel formed silica-based particles i.e. particles based on SiO_2 , preferably formed by polymerising silicic acid, encompassing both homopolymers and copolymers. Optionally the silica-based particles can be modified and contain other elements, e.g. amine, aluminium and/or boron, which can be present in the
10 aqueous phase and/or in the silica-based particles.

 Examples of suitable aggregated or microgel formed silica-based particles include colloidal silica, colloidal aluminium-modified silica or aluminium silicate, and different types of polysilicic acid and mixtures thereof, either alone or in combination with other types of anionic silica-based particles. In the art, polysilicic acid is also referred to as polymeric silicic
15 acid, polysilicic acid microgel, polysilicate and polysilicate microgel, which are all encompassed by the term polysilicic acid used herein. Aluminium-containing compounds of this type are commonly referred to as polyaluminosilicate and polyaluminosilicate microgel including colloidal aluminium-modified silica and aluminium silicate.

 The anionic silica-based particles are in the colloidal range of particle size. This
20 state comprises particles sufficiently small not to be affected by gravitational forces but sufficiently large not to show marked deviation from the properties of typical solutions, i.e. average particle size significantly less than 1 μm . The anionic silica-based particles have an average particle size suitably below about 50 nm, preferably below about 20 nm and more preferably in the range of from about 1 to about 50 nm, most preferably from about 1
25 up to about 10 nm. As conventional in silica chemistry, the particle size refers to the average size of the primary particles, which may be aggregated or non-aggregated. Suitably, the silica-based particles present in the aqueous silica-containing composition of the invention comprise aggregated or microgel formed silica-based particles, optionally and usually in combination with non-aggregated, or monodisperse, silica-based particles.

30 Suitably, the silica-based particles have a specific surface area larger than 50 m^2/g , preferably larger than 100 m^2/g . The specific area can be up to 1700 m^2/g , preferably up to 1300 m^2/g and usually in the range from 300 to 1300 m^2/g , preferably from 500 to 1050 m^2/g . The specific surface area can be measured by means of titration with NaOH according to the method described by Sears, Analytical Chemistry 28(1956), 12, 1981-1983 or in U.S.
35 Patent No. 5,176,891. The given area thus represents the average specific surface area of the particles.

 The total weight of the anionic organic polymer having at least one aromatic

group and anionic silica-based particles, calculated as SiO_2 , contained in the aqueous silica-containing composition is at least 0.01% by weight, calculated on the total weight of the aqueous silica-containing composition, preferably at least 0.05 % by weight, more preferably at least 0.1 % by weight. Suitably the concentration of the anionic organic polymer having at least one aromatic group and the anionic silica-based particles, calculated as SiO_2 , is within the range of 1 to 45% by weight, preferably within the range of 2 to 35 % by weight, most preferably 5 to 30% by weight.

The aqueous silica-containing composition can have an anionic charge density of at least 0.1 meq/g, usually the charge is within the range of from 0.1 to 10 meq/g, suitably within the range of from 0.1 to 8 meq/g, preferably within the range of from 0.1 to 6 meq/g, and most preferably within the range of from 0.2 to 4 meq/g.

The aqueous silica-containing composition according to the invention contains substantially no cellulose-reactive sizing agent. By substantially no means that less than or equal to 10% by weight, suitably less than 5%, preferably less than 1% by weight of cellulose-reactive sizing agent is present in the aqueous silica-containing composition. Most preferably there is no cellulose-reactive sizing agent in the aqueous silica-containing composition. Even more preferably, the aqueous silica-containing composition according to the invention contains substantially no sizing agent, suitably, contains no sizing agent.

The present invention relates further to a method for preparation of an aqueous silica-containing composition. The two components are preferably stirred together. The anionic organic polymer having at least one aromatic group can be added to an aqueous sol containing the silica-based particles or the silica-based particles can be added to an aqueous solution of anionic organic polymer having at least one aromatic group. The aqueous solution of anionic organic polymer having at least one aromatic group may be desalinated or deionised. The desalination or deionisation can be carried out with dialysis, membrane filtration, ultrafiltration, reversed osmosis or ion exchange or the like. It is preferred that the desalination or deionisation is carried out by the use of ultra-filtration or dialysis. The pH of an aqueous solution of anionic organic polymer may be adjusted to the pH of the silica-based particles, prior to or after mixing the aqueous solution with the silica-based particles. The pH can be adjusted to at least pH 8.0, suitably at least 9.0, preferably at least 9.5, preferably within the range of 9.0 to 11.0.

The anionic organic polymer having at least one aromatic group to be mixed with the silica-based particles can have an anionic charge density of at least 0.1 meq/g, usually within the range of from 0.1 to 10.0 meq/g of dry polymer, suitably within the range of from 0.2 to 6.0 and preferably within the range of from 0.5 to 4.0.

The silica-based particles, preferably anionic, to be mixed with the anionic organic polymer can have the previous mentioned properties. Suitably the silica-based particles are contained in a sol. The sol may have an S-value in the range of from 5 to 80%, suitably from 5 to 50%, preferably from 8 to 45%, and most preferably from 10 to 30%. Calculation
5 and measuring of the S-value can be performed as described by Iler & Dalton in J. Phys. Chem. 60(1956), 955-957. The S-value indicates the degree of aggregate or microgel formation and a lower S-value is indicative of a higher degree of aggregation.

Suitably, the silica-based particles comprise aggregated or microgel formed silica-based particles, optionally and usually in combination with non-aggregated, or monodispers,
10 silica-based particles.

Suitably the silica-based particles have a molar ratio $\text{Si}_2\text{O}:\text{Na}_2\text{O}$ less than 60, usually within the range 5 to 60, and preferably within the range from 8 to 55.

The aqueous silica-containing composition obtained by any of the methods according to the invention, contains suitably a total weight of the anionic organic polymer
15 having at least one aromatic group and anionic silica-based of at least 0.01% by weight, calculated on the total weight of the aqueous silica-containing composition, preferably at least 0.05 % by weight, more preferably at least 0.1 % by weight. Suitably the concentration of anionic organic polymer having at least one aromatic group and anionic silica-based particles is within the range of 1 to 45% by weight, preferably within the
20 range of 2 to 35 % by weight, most preferably 5 to 30% by weight.

The products prepared by any of these methods shows improved drainage and retention properties, and also a better storage stability and therefore a better drainage and retention aid performance when stored because it has a longer shelf life.

The mixing procedure of above mention methods is suitably carried out in the
25 presence of substantially no cellulose-reactive sizing agent. By substantially no means that less or equal to 10% by weight, suitably less than 5%, preferably less than 1% by weight of cellulose-reactive sizing agent is present. Most preferably there is no cellulose-reactive sizing agent present. The mixing procedure may also be carried out in the presence of substantially no sizing agent, or in the presence of no sizing agent.

30 The present invention further relates to a process for the production of paper from an aqueous suspension containing cellulosic fibres. The process comprises adding to the suspension a cationic organic polymer and the aqueous silica-containing composition of the invention. The cationic organic polymer according to the invention can be linear, branched or cross-linked. Preferably the cationic polymer is water-soluble or
35 water-dispersible.

Examples of suitable cationic polymers include synthetic organic polymers, e.g. step-growth polymers and chain-growth polymers, and polymers derived from natural sources, e.g. polysaccharides.

5 Examples of suitable cationic synthetic organic polymers include vinyl addition polymers such as acrylate- and acrylamide-based polymers, as well as cationic poly(diallyl dimethyl ammonium chloride), cationic polyethylene imines, cationic polyamines, polyamidoamines and vinylamide-based polymers, melamine-formaldehyde and urea-formaldehyde resins.

10 Examples of suitable polysaccharides include starches, guar gums, cellulose derivatives, chitins, chitosans, glycans, galactans, glucans, xanthan gums, pectins, mannans, dextrans, preferably starches and guar gums. Examples of suitable starches include potato, corn, wheat, tapioca, rice, waxy maize, barley, etc.

Cationic starches and cationic acrylamide-based polymers are preferred polymers according to the invention, and they can be used singly, together with each other or together with other polymers, particularly preferred are cationic starches and
15 cationic acrylamide-based polymers having at least one aromatic group.

The cationic organic polymers can have one or more hydrophobic groups attached to them. The hydrophobic groups can be aromatic groups, groups comprising aromatic groups or non-aromatic groups, preferably the hydrophobic groups comprise
20 aromatic groups. The hydrophobic group can be attached to a heteroatom, e.g. nitrogen or oxygen, the nitrogen optionally being charged, which heteroatom, it can be attached to the polymer backbone, for example via a chain of atoms. The hydrophobic group may have at least 2 and usually at least 3 carbon atoms, suitably from 3 to 12 and preferably from 4 to 8 carbon atoms. The hydrophobic group is suitably a hydrocarbon chain.

25 Suitable dosages counted as dry substance based on dry pulp and optional filler, of the cationic polymer in the system is from 0.01 to 50 kg/t (kg/tonne, "metric ton") of, preferably from 0.1 to 30 kg/t and most preferably from 1 to 15 kg/t.

Suitable dosages counted as dry substances based on dry pulp and optional filler, of the aqueous silica-containing composition defined above in the system are from
30 0.01 to 15 kg/t, preferably from 0.01 to 10 kg/t calculated as an anionic organic polymer having at least one aromatic group and anionic silica-based particles, and most preferably from 0.05 to 5 kg/t.

Suitable mineral fillers of conventional types may be added to the aqueous cellulosic suspension according to the invention. Examples of suitable fillers include
35 kaolin, china clay, titanium dioxide, gypsum, talc and natural and synthetic calcium carbonates such as chalk, ground marble and precipitated calcium carbonate (PCC).

Further additives that are conventional in papermaking can of course be used in combination with the chemicals according to the invention, for example anionic trash

catchers (ATC), wet strength agents, dry strength agents, optical brightening agents, dyes, aluminium compounds, etc. Examples of suitable aluminium compounds include alum, aluminates, aluminium chloride, aluminium nitrate, and polyaluminium compounds, such as polyaluminium chlorides, polyaluminium sulphates, polyaluminium compounds containing chloride and/or sulphate ions, polyaluminium silicate sulphates, and mixtures thereof. The polyaluminium compounds may also contain other anions than chloride ions, for example anions from sulfuric acid, phosphoric acid, or organic acids such as citric acid and oxalic acid. When employing an aluminium compound in the present process, it is usually preferably to add it to the stock prior to the polymer component and micro- or nano-particulate material. Suitable addition levels of aluminium containing compounds is at least 0.001 kg/t, preferably from 0.01 to 5 kg/t and more preferably from 0.05 to 1 kg/t, calculated as Al_2O_3 based on dry pulp and optional filler.

Examples of suitable anionic trash catchers include cationic polyamines, polymers or copolymers of quaternary amines, or aluminum containing compounds.

The process of this invention is used for the production of paper. The term "paper", as used herein, include not only paper and the production thereof, but also other web-like products, such as for example board and paperboard, and the production thereof. The invention is particularly useful in the manufacture of paper having grammages below 150 g/m^2 , preferably below 100 g/m^2 , for example fine paper, newspaper, light weight coated paper, super calendered paper and tissue.

The process can be used in the production of paper from all types of stocks, both wood containing and woodfree. The different types of suspensions of cellulose-containing fibres and the suspensions should suitably contain at least 25% by weight and preferably at least 50% of weight of such fibres, based on dry substance. The suspensions comprise fibres from chemical pulp such as sulphate, sulphite and organosolv pulps wood-containing or mechanical pulp such as thermomechanical pulp, chemo-thermomechanical pulp, refiner pulp and groundwood pulp, from both hardwood and softwood, and can also be based on recycled fibres, optionally from de-inked pulps, and mixtures thereof. Preferably the stock is a wood containing stock, which have high contents of salts (high conductivity).

The chemicals according to the present invention can be added to the aqueous cellulosic suspension, or stock, in conventional manner and in any order. It is usually preferably to add the cationic polymer to the stock before adding the aqueous silica-containing composition, even if the opposite order of addition may be used. It is further preferred to add the cationic polymer before a shear stage, which can be selected from pumping, mixing, cleaning, etc., and to add the aqueous silica-containing composition after that shear stage.

The aqueous silica-containing composition can be used as a flocculation agent in the treatment of water for the production of drinking water or as an environmental treatment

of waters for instance in lakes. The composition can also be used as flocculation agent in the treatment of wastewater or waste sludges.

The invention is further illustrated in the following examples, which are not intended to limit the scope thereof. Parts and % relate to parts by weight and % by weight, respectively, and all solutions are aqueous, unless otherwise stated. The units are metric.

Example 1

Drainage performance was evaluated by means of a Dynamic Drainage Analyser (DDA), available from Akribi, Sweden. The drainage time was measured on a set volume of stock through a wire when removing a plug and applying vacuum to that side of the wire opposite to the side on which the stock is present.

Retention performance was evaluated by means of a nephelometer by measuring the turbidity of the filtrate, the white water, obtained by draining the stock. The turbidity was measured in NTU (Nephelometric Turbidity Units).

The test stock was wood containing with a pH 7.2, the conductivity of the stock was 5.0 mS/cm, and the consistency was 1.42 g/l. The stock was stirred in a baffled jar at a speed of 1500 rpm throughout the test.

In the example a cationic polymer was added to the stock before the aqueous compositions according to the invention or the anionic reference. The cationic polymer was a cationic starch (C1) obtained by quarternisation of native potato starch with 3-chloro-2-hydroxypropyl dimethyl benzyl ammonium chloride to 0.5% N was added followed by 45 seconds of stirring, and then the anionic aqueous composition was added, followed by 15 seconds stirring before drainage.

Aqueous compositions according to the invention containing anionic polyurethane and colloidal silica were measured to evaluate their drainage and retention performance. All samples were diluted to 0.5% of solids before the evaluation of drainage properties. The anionic polyurethane (P1) is based on an anionic polyurethane of 15% solids, produced from glyceryl monostearate (GMS) and toluolyl diisocyanate (TDI), which forms a pre-polymer, which is reacted with dimethylol propionic acid (DMPA), with 30 mol% of GMS is replaced by DPMA / N-methyl diethanol amine (N-MDEA). The colloidal silica sol (S1) is of the type described in US 5,447,604 having a molar ratio $\text{SiO}_2:\text{Na}_2\text{O}$ of 10, specific surface area of 870 m^2/g , S-value of 35% and silica content of 10.0% by weight. The drainage time measured on the stock with addition of 20 kg/t of C1 was 29 seconds and the turbidity was measured to 44 NTU. All additions are calculated as dry on dry stock. The drainage times derived from the different additions to the stock of the aqueous composition of the invention are summarised in Table 1.

Table 1

Sample	Ratio	Drainage time (sec) / Turbidity (NTU) at dosage of
--------	-------	--

13

		4 kg/t	6 kg/t	8 kg/t	10 kg/t
S1		19.7 / 35	16.9 / 31	15.6 / 30	16.0 / 29
P1		17.7 / 34	15.3 / 33	14.0 / 32	13.9 / 32
S1/P1	4:1	17.3 / 33	14.0 / 30	13.5 / 28	14.0 / 27
S1/P1	1:1	16.4 / 34	13.6 / 30	13.0 / 28	13.1 / 28
S1/P1	1:4	16.5 / 33	13.9 / 31	13.3 / 29	12.9 / 29

The drainage times and turbidity for the composition S1/P1 show that when the two components (S1 and P1) are added as a composition they have a synergistic improvement on the drainage and retention performance.

Example 2

- 5 The aqueous compositions according to the invention containing anionic polyurethane (P2) based on an anionic polyurethane of 19% solids, produced from TDI and phenyl diethanol amine PDEA, which forms the pre-polymer, which is reacted with a mixture of DMPA and N-MDEA and of which 30 mol% of PDEA is replaced by DPMA/N-MDEA, and a colloidal silica (S2) having a molar ratio $\text{SiO}_2:\text{Na}_2\text{O}$ of 20, specific surface
- 10 area of 700 m^2/g , S-value of 32% and silica content of 15.0%, were evaluated for drainage and retention performance. All the samples were diluted to 0.5% solids before the drainage and retention evaluation, which was performed exactly in the same manner as in Example 1 and with the same cationic starch in the same stock. The drainage time
- 15 was measured to 45 NTU. All additions are calculated as dry on dry stock. The drainage times derived from the different additions to the stock of the aqueous composition of the invention are summarised in Table 2.

Table 2

Sample	Ratio	Drainage time (sec) / Turbidity (NTU) at dosage of			
		2 kg/t	4 kg/t	6 kg/t	8 kg/t
S2		21.0 / -	15.7 / -	12.4 / -	12.9 / -
P2		21.8 / 44	18.0 / 39	12.9 / 31	12.0 / 29
S2 / P2	4:1	21.0 / 40	15.5 / 31	12.0 / 28	10.4 / 27
S2 / P2	1:1	-	13.8 / 30	11.0 / 27	9.8 / 27
S2 / P2	1:4	-	13.3 / 32	11.0 / 29	10.3 / 27

20

Example 3

In this example the test stock was SC-furnish (furnish for Super Calandered paper) with a pH 7.6, the conductivity of the stock was 0.5 mS/cm, and the consistency

was 1,49 g/l. The stock was stirred in a baffled jar at a speed of 1500 rpm throughout the test. C1 was added to the stock in an amount of 20kg/t (kg/tonne) in each test. The drainage time measured on the stock without any additives was 30 seconds and the turbidity was 98 NTU, the drainage time on the stock with addition of C1 only was 14.8
 5 seconds and the turbidity was measured to 52 NTU. The anionic polyurethane used in this example was an anionic polyurethane (P3) of 15% solids, produced from GMS and TDI, which forms a pre-polymer, which is reacted DMPA and the colloidal silica (S3) described in US 5,368,833 was a silica sol having a molar ratio $\text{SiO}_2:\text{Na}_2\text{O}$ of 45, specific surface area of 850 m^2/g , S-value of 20% and a silica content of 8.0%, and was modified
 10 with aluminium to 0.3% Al_2O_3 .

The performance of the aqueous composition according to the invention was compared to the performance of the components added separately. In all tests C1 was added to the stock followed by 45 seconds of stirring, then the composition S3/P3 was added followed by 15 seconds of stirring. When the components were added separately
 15 the first component was added followed by 30 seconds of stirring and the second components was added followed by 15 seconds of stirring. All additions are calculated as dry on dry stock. The drainage times derived from the different additions to the stock are summarised in Table 3.

20

Table 3

Sample	Ratio	Drainage time (sec) / Turbidity (NTU) at dosage of			
		1 kg/t	2 kg/t	3 kg/t	4 kg/t
C1 + S3		-	-	-	10.2 / 56
C1 + P3		13.9 / 54	13.0 / 55	12.0 / 56	13.0 / 55
C1+ S3 / P3	1:1	12.6 / 52	11.4 / 51	10.0 / 58	10.0 / 55
C1+ S3 / P3	3:1	12.2 / 52	11.1 / 54	10.7 / 55	10.4 / 55
C1+ S3 / P3	1:3	12.9 / 52	12.1 / 55	11.6 / 54	-
C1+S3+P3	1:1	-	-	-	12.4 / 53
C1+P3+S3	1:1	-	-	-	12.4 / 55

Example 4

The aqueous compositions according to the invention containing a 10% solution of an anionic lignosulphonate (LS1), which is the sodium salt of sulphonated and
 25 carboxylated Kraft lignin derived from soft wood, having a dry matter of 89.0% by weight, pH of 10.5, a sodium content of 9.5%, and a total sulphur content of 5.4%, wherein sulphur is bound to 4.2%, or a 10% solution anionic lignosulphonate (LS2), which is a

sodium oxygignin derived from fermented spruce wood sulphite liquor, having a dry matter of 93.0% by weight, pH of 8.5, a sodium content of 8%, and sulphur content of 3%, and colloidal silica S1, were evaluated for drainage and retention performance. All the samples were diluted to 0.5% solids before the drainage evaluation. The drainage time measured on the stock with addition of 20 kg/t of C1 was 29 seconds and the turbidity was measured to 44 NTU. All additions are calculated as dry on dry stock. The drainage times derived from the different additions to the stock of the aqueous composition of the invention are summarised in Table 4.

Table 4

Sample	Ratio	Drainage time (sec) / Turbidity (NTU) at dosage of					
		2 kg/t	4 kg/t	6 kg/t	8 kg/t	10 kg/t	12 kg/t
S1		23.5/38	19.7/35	16.9/31	15.6/30	16.0/29	-
LS1		-	21.9/35	18.8/34	17.5/33	17.2/32	-
LS2		-	22.5/-	19.9/36	17.9/35	17.8/34	18.5/-
S1 / LS1	4:1	-	18.5/-	15.3/29	14.4/26	14.5/25	-
S1 / LS1	1:1	-	18.8/-	15.5/30	13.1/30	12.8/31	-
S1 / LS2	4:1	-	18.4/-	15.1/31	13.2/28	12.5/27	12.4/25
S1 / LS2	1:1	-	19.2/-	15.8/33	13.8/28	12.8/25	12.1/26

CLAIMS

1. An aqueous silica-containing composition comprising an anionic organic polymer having at least one aromatic group and anionic silica-based particles comprising aggregated or microgel formed silica-based particles, the aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the anionic silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight based on the total weight of the aqueous silica-containing composition, with the proviso that the composition contains substantially no cellulose-reactive sizing agent and the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

2. An aqueous silica-containing composition obtainable by mixing an anionic organic polymer having at least one aromatic group with an aqueous alkali stabilised silica-based sol having an S-value in the range of from about 5 up to about 50% containing anionic aggregated or microgel formed silica-based particles, to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition, with the proviso that the composition contains substantially no cellulose-reactive sizing agent and that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

3. A method for preparation of an aqueous silica-containing composition which comprises mixing in the presence of substantially no cellulose-reactive sizing agent an anionic organic polymer having at least one aromatic group with silica-based particles comprising anionic aggregated or microgel formed silica-based particles to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition with the proviso that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

4. A method for preparation of an aqueous silica-containing composition which comprises mixing an anionic organic polymer having at least one aromatic group and a charge density of at least 0.1 meq/g of dry polymer, with anionic silica-based particles comprising aggregated or microgel formed silica-based particles to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on the total weight of the aqueous silica-containing composition,

with the proviso that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

5 5. A method for preparation of an aqueous silica-containing composition which comprises desalinating an aqueous solution of an anionic organic polymer having at least one aromatic group, mixing the desalinated anionic organic polymer having at least one aromatic group with anionic silica-based particles comprising aggregated or microgel formed silica-based particles to provide an aqueous silica-containing composition containing the anionic organic polymer having at least one aromatic group and the silica-based particles, calculated as SiO_2 , in an amount of at least 0.01 % by weight, based on
10 the total weight of the aqueous silica-containing composition with the proviso that the anionic organic polymer having at least one aromatic group is not an anionic naphthalene sulphonate formaldehyde condensate.

6. The method according to any of claims 3 to 5, wherein the silica-based particles are contained in a silica sol having an S-value within the range of from about 5
15 up to about 50% prior to mixing with the anionic organic polymer having at least one aromatic group.

7. The method according to any of the preceding claims, wherein the anionic organic polymer having at least one aromatic group is desalinated prior to mixing with the silica-based particles.

20 8. The aqueous silica-containing composition according to claims 1 or 2, or the method according to any of claims 3 to 7, wherein the silica-based particles have a specific surface area within the range of from 300 to 1300 m^2/g .

9. The aqueous silica-containing composition according to any of claims 1, 2 or 8, or the method according to any of claims 3 to 8, wherein the silica-based particles have
25 an average particle size ranging from about 1nm up to about 50 nm.

10. The aqueous silica-containing composition according to any of claims 1, 2, 8, or 9 or the method according to any of claims 3 to 9, wherein the silica-based particles have an average particle size ranging from about 1nm up to about 10 nm.

11. The aqueous silica-containing composition according to any of claims 1, 2,
30 8, 9 or 10, or the method according to any of claims 3 to 10, wherein pH of the aqueous solution of the anionic organic polymer having at least one aromatic group is adjusted to a pH of at least 8 prior to mixing with the silica-based particles.

12. The aqueous silica-containing composition according to any of claims 1, 2, 8, 9, 10 or 11, or the method according to any of claims 3 to 11, wherein the anionic
35 organic polymer having at least one aromatic group is a polyurethane, lignosulphonate, Kraft lignin or oxygignin.

13. The aqueous silica-containing composition according to any of claims 1, 2, 8, 9, 10, 11 or 12 or the method according to any of claims 3 to 12, wherein the aqueous silica-containing composition has a negative charge density within the range of from 0.1 to 6 meq/g.

5 14. An aqueous silica-containing composition obtainable by the method according to any claims 3 to 13.

15. Use of an aqueous silica-containing composition according to any of claims 1, 2, 8, 9, 10, 11, 12, 13 or 14 as a flocculating agent in combination with at least one organic polymer in the production of pulp and paper and for water purification.

10 16. A process for the production of paper from a suspension containing cellulosic fibres, and optionally fillers, comprising adding to the suspension at least one cationic organic polymer and an aqueous silica-containing composition according to any of claims of 1, 2, 8, 9, 10, 11, 12, 13 or 14 adding an aqueous silica-containing composition obtained by the method according to any of claims 3 to 11.

15 17. The process according to claim 14, wherein the cationic organic polymer being cationic starch or cationic polyacrylamide.

18. The process according to claim 14 or 15, wherein the cationic organic polymer having at least one aromatic group.

20 19. The aqueous silica-containing composition according to claim 1 or 2, with the proviso that the composition contains substantially no sizing agent.

20. The method according to claim 3, wherein the mixing is carried out in the presence of substantially no sizing agent.

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/SE 02/02444A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D21H17/68 D21H21/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 418 015 A (ALBRIGHT & WILSON) 20 March 1991 (1991-03-20) cited in the application	2, 4, 5, 12, 14, 16
Y	claims 1-15; examples 1-19	1, 3
X	US 5 670 021 A (OWENS MICHAEL) 23 September 1997 (1997-09-23)	2, 4, 5, 14-16
Y	claims 1-10; example 3	1, 3
X	US 6 033 524 A (JAKUBOWSKI REGINA ET AL) 7 March 2000 (2000-03-07)	2, 12, 15
Y	claims 1-18	1
X	US 6 315 824 B1 (LAUZON RODRIGUE V) 13 November 2001 (2001-11-13)	2
Y	claims 1-3, 5, 6	1
	-/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

17 April 2003

Date of mailing of the international search report

08/05/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Karlsson, L

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/SE 02/02444

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 953 680 A (AKZO NOBEL NV) 3 November 1999 (1999-11-03) paragraph '0021! ---	1, 3
A	EP 0 752 496 A (EKA CHEMICALS AB) 8 January 1997 (1997-01-08) the whole document ---	1-20
A	US 5 185 062 A (BEGALA ARTHUR J) 9 February 1993 (1993-02-09) the whole document ---	1-20
A	US 4 313 790 A (PELTON ROBERT H ET AL) 2 February 1982 (1982-02-02) the whole document ---	1-20
A	US 6 165 259 A (FROELICH STEN ET AL) 26 December 2000 (2000-12-26) the whole document ---	1-20
A	EP 0 308 752 A (NALCO CHEMICAL CO) 29 March 1989 (1989-03-29) the whole document -----	1-20

INTERNATIONAL SEARCH REPORT

Information on patent family members

International App No

PCT/SE 02/02444

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0418015	A	20-03-1991	AU 6231790 A	14-03-1991
			BR 9004518 A	10-09-1991
			CA 2024975 A1	12-03-1991
			EP 0418015 A1	20-03-1991
			JP 3167391 A	19-07-1991
			NO 903926 A	12-03-1991
			ZA 9007216 A	31-07-1991
US 5670021	A	23-09-1997	AU 3466593 A	01-09-1993
			FI 943549 A	28-09-1994
			NO 942808 A	28-09-1994
			WO 9315271 A1	05-08-1993
US 6033524	A	07-03-2000	WO 0049227 A1	24-08-2000
			AU 4223299 A	04-09-2000
			CA 2315676 A1	28-11-2000
			EP 1104495 A1	06-06-2001
			JP 2002537498 T	05-11-2002
			NZ 505246 A	28-03-2002
US 6315824	B1	13-11-2001	US 5846308 A	08-12-1998
			AU 2041700 A	26-06-2000
			BR 9916022 A	28-08-2001
			CA 2353400 A1	15-06-2000
			CN 1334888 T	06-02-2002
			EP 1137848 A1	04-10-2001
			JP 2002531727 T	24-09-2002
			NO 20012780 A	02-08-2001
			NZ 512163 A	27-09-2002
			WO 0034583 A1	15-06-2000
			AU 710273 B2	16-09-1999
			AU 1711097 A	22-08-1997
			BR 9707265 A	13-04-1999
			CA 2245507 A1	07-08-1997
			CN 1215444 A, B	28-04-1999
			EP 0877840 A1	18-11-1998
			IL 125611 A	11-01-2001
			JP 2000504787 T	18-04-2000
			NO 983497 A	25-09-1998
			NZ 331188 A	25-11-1998
			WO 9728311 A1	07-08-1997
			ZA 9700785 A	04-08-1997
EP 0953680	A	03-11-1999	EP 0953680 A1	03-11-1999
			AU 750335 B2	18-07-2002
			AU 4301499 A	16-11-1999
			AU 748735 B2	13-06-2002
			AU 4401599 A	16-11-1999
			AU 747089 B2	09-05-2002
			AU 4401699 A	16-11-1999
			BR 9909945 A	26-12-2000
			BR 9909946 A	06-03-2001
			BR 9909947 A	26-12-2000
			CA 2329027 A1	04-11-1999
			CA 2329028 A1	04-11-1999
			CA 2329191 A1	04-11-1999
			CN 1298466 T	06-06-2001
			CN 1299425 T	13-06-2001

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/SE 02/02444

Patent document cited in search report		Publication date	Patent family member(s)	Publication date		
EP 0953680	A		CN 1300332 T	20-06-2001		
			CZ 20003937 A3	12-12-2001		
			CZ 20003939 A3	12-12-2001		
			EP 1080272 A1	07-03-2001		
			EP 1080271 A1	07-03-2001		
			EP 1084295 A2	21-03-2001		
			JP 2002513102 T	08-05-2002		
			JP 2002513103 T	08-05-2002		
			JP 2002513104 T	08-05-2002		
			NO 20005240 A	22-12-2000		
			NO 20005241 A	22-12-2000		
			NO 20005242 A	27-12-2000		
			NZ 507605 A	31-01-2003		
			PL 344040 A1	24-09-2001		
			PL 344053 A1	24-09-2001		
			PL 344079 A1	24-09-2001		
			RU 2194106 C2	10-12-2002		
			RU 2194818 C2	20-12-2002		
			RU 2185470 C1	20-07-2002		
			WO 9955965 A1	04-11-1999		
			WO 9955962 A2	04-11-1999		
			WO 9955964 A1	04-11-1999		
			US 2002139502 A1	03-10-2002		
		EP 0752496	A	08-01-1997	AT 207989 T	15-11-2001
					AU 691428 B2	14-05-1998
					AU 5830096 A	23-01-1997
					BR 9602943 A	28-04-1998
CA 2180404 A1	08-01-1997					
CN 1145967 A ,B	26-03-1997					
DE 69616439 D1	06-12-2001					
DE 69616439 T2	11-07-2002					
DK 752496 T3	21-01-2002					
EP 0752496 A2	08-01-1997					
ES 2166424 T3	16-04-2002					
JP 9031885 A	04-02-1997					
NO 962845 A	08-01-1997					
NZ 286923 A	22-09-1997					
PL 315106 A1	20-01-1997					
PT 752496 T	28-02-2002					
RU 2121538 C1	10-11-1998					
US 6100322 A	08-08-2000					
US 5858174 A	12-01-1999					
ZA 9605610 A	27-01-1997					
US 5185062	A	09-02-1993	US 5098520 A	24-03-1992		
			AT 114178 T	15-12-1994		
			AU 656541 B2	09-02-1995		
			AU 8831991 A	30-07-1992		
			DE 69105193 D1	22-12-1994		
			DE 69105193 T2	18-05-1995		
			DK 497030 T3	18-04-1995		
			EP 0497030 A1	05-08-1992		
			ES 2067155 T3	16-03-1995		
			FI 913469 A ,B,	26-07-1992		
			GR 3014980 T3	31-05-1995		
			JP 2831165 B2	02-12-1998		
			JP 4245998 A	02-09-1992		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/SE 02/02444

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5185062	A	KR 171200 B1 NO 912841 A , B,	30-03-1999 27-07-1992
US 4313790	A	02-02-1982 NONE	
US 6165259	A	26-12-2000	
		AT 225437 T	15-10-2002
		AT 225436 T	15-10-2002
		AT 225435 T	15-10-2002
		AU 729667 B2	08-02-2001
		AU 6009998 A	25-08-1998
		AU 729833 B2	08-02-2001
		AU 6010098 A	25-08-1998
		AU 729702 B2	08-02-2001
		AU 6010198 A	25-08-1998
		BR 9807040 A	28-03-2000
		BR 9807049 A	28-03-2000
		BR 9807978 A	15-02-2000
		CN 1280640 T	17-01-2001
		CN 1246899 T	08-03-2000
		CN 1246900 T	08-03-2000
		DE 69808435 D1	07-11-2002
		DE 69808436 D1	07-11-2002
		DE 69808437 D1	07-11-2002
		DK 963484 T3	20-01-2003
		DK 961855 T3	20-01-2003
		EP 0963485 A2	15-12-1999
		EP 0963484 A1	15-12-1999
		EP 0961855 A1	08-12-1999
		ES 2183323 T3	16-03-2003
		ES 2183324 T3	16-03-2003
		ES 2183325 T3	16-03-2003
		JP 3268582 B2	25-03-2002
		JP 2000509447 T	25-07-2000
		JP 3175774 B2	11-06-2001
		JP 2000509448 T	25-07-2000
		JP 2000509430 T	25-07-2000
		NO 993740 A	28-09-1999
		NO 993741 A	27-09-1999
		NO 993742 A	29-09-1999
		NZ 336572 A	26-01-2001
		NZ 336786 A	23-02-2001
		NZ 336787 A	28-04-2000
		PT 963484 T	31-01-2003
		PT 961855 T	31-01-2003
		SK 102599 A3	14-08-2000
		SK 103099 A3	16-05-2000
		US 5969011 A	19-10-1999
		US 6093217 A	25-07-2000
		US 6306255 B1	23-10-2001
		RU 2168579 C2	10-06-2001
		WO 9833980 A1	06-08-1998
		WO 9833979 A1	06-08-1998
EP 0308752	A	29-03-1989	
		US 4795531 A	03-01-1989
		AU 2243688 A	23-03-1989
		BR 8804878 A	25-04-1989
		CA 1321046 A1	10-08-1993
		DE 3886491 D1	03-02-1994

INTERNATIONAL SEARCH REPORT
 information on patent family members

International application No
PCT/SE 02/02444

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0308752	A	DE 3886491 T2	07-07-1994
		DE 308752 T1	28-12-1989
		EP 0308752 A2	29-03-1989
		ES 2010968 T3	16-02-1994
		FI 884339 A ,B	23-03-1989
		JP 1162897 A	27-06-1989
		JP 2922907 B2	26-07-1999
		NO 884187 A ,B,	28-03-1989
		NZ 226240 A	27-10-1989

This Page Blank (uspto)